# Dr. Fixit Pidiproof LW+



# INTEGRAL LIQUID WATERPROOFING COMPOUND FOR CONCRETE & PLASTER

#### Description

**Dr. Fixit Pidiproof LW+** is specially formulated integral liquid waterproofing compound composed of surface active plasticising agents, polymers & additives. It is used as an additive for cement concrete, mortar & plasters. It makes concrete cohesive and prevents segregation.

### **Typical Application**

# Waterproofing of concrete and sand-cement mortars used in

- Basements.
- Roof slabs and screeds,
- Water tanks & water retaining structures,
- External plastering,
- Bathrooms and balconies,
- Sumps and drains

#### **Features**

- Corrosion resistant Makes concrete more cohesive, hence protects steel better against corrosion
- Compatibility Being a liquid, easily dispersible & compatible with concrete/mortar mixes.
- Permeability It reduces the permeability of water into concrete.
- Strength The setting time and compressive strength of the concrete remains within the specification limits.
- Shrinkage Reduces shrinkage crack development in plaster & concrete.
- Workability Improves workability of freshly mixed cement concrete.
- Durability Increases durability by improving waterproofing of concrete.

#### **Packing**

200 ml, 1, 5, 10, 20 & 100 litre

# Method of Application

- Charge cement & aggregates to concrete mixer as per the mix design, mix in dry state for 1-2 minutes.
- Start addition of 75-80% mixing water & mix for 2-3 minutes.
- Dr. Fixit Pidiproof LW+ is added as per the recommended dosage into the remaining mixing / gauging water, then add to concrete mixer & mix for another 2 minutes.
- Place the concrete or apply plaster, as needed.
- Cure the applied mortar or concrete as per good construction practices.

#### **Precautions & Limitations**

- Do not add Dr. Fixit Pidiproof LW+ directly to dry cement & aggregate mix.
- Maintain water-cement ratio as low as possible.
- Do not increase the dosage of Dr. Fixit Pidiproof LW+ than the recommendation.



# **Technical Information**

| PROPERTIES                  | SPECIFICATION  | RESULTS             |
|-----------------------------|----------------|---------------------|
|                             |                |                     |
| Appearance                  |                | Free flowing liquid |
| Colour                      |                | Wine red            |
| Sp. gr. @ 25°C              |                | 1.04 - 1.09         |
| Non volatile content        |                | 13.5 - 14.5%        |
| pH value                    |                | 11.0 - 14.0         |
| Setting time, minutes       | IS: 2645: 2003 | Passes              |
| Chloride content            | IS: 2645: 2003 | 0.03%               |
| Water permeability          | IS: 2645: 2003 | Passes              |
| Compressive strength N /mm² | IS: 2645: 2003 | As per the standard |

#### Dosage

200 ml per 50 kg bag of cement

#### Shelf Life

- Best before 2 years from the date manufacture when in sealed pack and stored under proper condition.
- Store in a cool & dry place.

# Health & Safety

- Use rubber hand gloves & safety goggles, while using Dr. Fixit Pidiproof LW+.
- In case of contact with skin, wash with plenty of water.
- Keep out of reach of children

### Other Products Categories available

Dr. Fixit brings you the widest range of Construction Chemicals



















Pidilite Industries Limited Construction Chemicals Division Ramkrishna Mandir Road, Post Box No. 17411 Andheri (E) Mumbai 400059 INDIA Tel+91-22-2835 7000 · Fax +91-22-2835 7008 www.drfixit.co.in · info.drfixit@pidilite.com

Dr. Fixit Advice Centre (Toll Free No.) 1800 209 5504

DISCLAIMER The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.